



DESCRIPTION

FACADE COATING P10 is a white powder coating, containing hydraulic binders. It is a finishing plaster, which allows the smoothing of walls and masonry repairs in facade work.

FIELD OF USE

Powder coating and repair coating, for manual application.

TECHNICAL CHARACTERISTICS

- Aspect : Powder.
- Color : White.
- Spreading-rate : 2 to 3 kg / m², dry thickness from 1.5 to 3.0 mm depending on the load, in accordance with ISO 23811 (2009).

SURFACE PREPARATION

The work must be done in accordance with standard NF DTU59.1 and will be carried out with the greatest care.

CONDITIONS AND METHODS OF APPLICATION

Recommended material: Coating knife.
If the substrate is damp, remove the source of moisture and apply a water-repellent print with a coat of Coloprime. Once the surface is dry, apply a thin layer of our P10 Facade Coating with a knife to fill the holes and obtain a regular surface. Application limit: Do not apply on condensing or frozen substrates, at temperatures below 5 °C, or at relative humidity above 70%.

APPLICATION DETAILS OF USAGE

Impatage with clear water.

DRYING TIME

Drying at 20 °C and 60% humidity:
*Dust free: 15 min.
*Dry: 12 hours.
*Interval between coats: 24 Hours Drying.
Up to 2 cm in 2 layers (1cm / layer).

RECOMMENDED SYSTEM

■ INTERIOR

SYSTEM	NUMBER OF COATS
ENDUIT P10	1/2
COLOPRIM or COLOFIX	1
FINISHING PAINT	2

■ EXTERIOR

SYSTEM	NUMBER OF COATS
ENDUIT P20	1/2
ENDUIT P10	1/2
COLOPRIM or COLOFIX	1
FINISHING PAINT	2

STORAGE

The product can be stored for up to 2 years in good storage conditions away from sunlight, it is nevertheless recommended to shake the product before use.

PACKAGING

5 kg, 25 kg.

HEALTH & SAFETY

Health and safety information and precautions for use are detailed on the safety data sheet N°259.

Edition : July 2020 by Colorado 07/20 (DC28 D).

N.B : The purpose of this technical data sheet is to provide information on the properties of our product. The information contained therein is based on our current knowledge of tests carried out with a constant concern for objectivity according to the conditions of use in accordance with standards or DTU in force; However, the information cannot replace an appropriate description and the state of the funds to be painted. This descriptive technical sheet cancels and replaces any sheet relating to the same product. The above technical data does not imply acceptance of the guarantees. Close the pot tightly after use. Help preserve the environment by not disposing of waste in the drains or household waste. Please return your empty jar to a recycling center. For your unused product, please contact your local authorities for information on disposal and collection.

COLORADO is certified ISO 9001, ISO 14001 and ISO 45001