



DESCRIPTION

FINIROUILLE is a fast drying alkyd resin based anticorrosive primer for iron and ferrous metals, free from rust and grease.

FIELD OF USE

Protection of ferrous supports such as metal frames, works of art or more simply metal joinery such as grids, gates, garden furniture ...

FINIROUILLE provides the anti-rust function after mechanical brushing to remove the layer of rust formed.

TECHNICAL CHARACTERISTICS

- Aspect : Matt -satin.
- Spreading-rate : 6 to 7 m²/Kg
- Density : Grey : 1,60 +/- 0,05 Kg/L at 25°C
Red brown : 1,55 +/- 0,05 kg/L at 25°C .
- Dry extract by volume : Grey : 68 +/- 2 %.
Red brown : 51 -/+ 2%.

SURFACE PREPARATION

The work must be done in accordance with standard NF DTU59.1 and will be carried out with the greatest care.

APPLICATION PROPERTIES

Application equipment: Brush, roller, or pneumatic gun. Take all measures to protect the immediate environment of the site in the event of mechanical application. Application: After homogenization of the product, apply regularly by crossing and smoothing in a uniform manner, with particular emphasis in the first coat on sensitive points (welds, rivets etc.).

Application conditions: Do not apply at temperature below + 8 ° C or above + 30 ° C, strong wind, frozen, condensing, overheated substrates or in borderline climatic conditions (fog, threatening rains, risk of night frosts). Relative humidity less than 70%.

APPLICATION DETAILS OF USAGE

A 5 to 15% dilution of synthetic diluent: solvent D66 is recommended.

DRYING TIME

Drying at 20 ° C and 60% humidity:

- * Dust free: 1 hour.
- * Dry to touch: 4 hours.
- * Hard to heart: 12 hours.
- * Recovery time: 24 hours minimum.

RECOMMENDED SYSTEM

■ METAL

| SYSTEM | NUMBER OF COATS |
|-----------------|-----------------|
| Iron metals | Remove rust |
| FINIROUILLE | 2 |
| Finishing paint | 2 |

STORAGE

The product can be stored for up to 1 year in good storage conditions away from sunlight, it is nevertheless recommended to shake the product before use.

PACKAGING

1 Kg, 5 Kg.

HEALTH & SAFETY

Health and safety information and precautions for use are detailed in the safety data sheet N°295.

Edition : November 2020 by Colorado 11/20 (DC28 D).

N.B : The purpose of this technical data sheet is to provide information on the properties of our product. The information contained therein is based on our current knowledge of tests carried out with a constant concern for objectivity according to the conditions of use in accordance with standards or DTU in force; However, the information cannot replace an appropriate description and the state of the funds to be painted. This descriptive technical sheet cancels and replaces any sheet relating to the same product. The above technical data does not imply acceptance of the guarantees. Close the pot tightly after use. Help preserve the environment by not disposing of waste in the drains or household waste. Please return your empty jar to a recycling center. For your unused product, please contact your local authorities for information on disposal and collection.

COLORADO is certified ISO 9001, ISO 14001 and ISO 45001