



67E5D;BF;A@

Decorative coating in aqueous phase, pearlescent and sandblasted effect.

FIELD OF USE

Specially designed to enhance interiors and furnishings with a particularly warm atmosphere.

TECHNICAL CHARACTERISTICS

- Aspect : Pearly and finely sanded.
- Colors: Available in 32 shades according to our catalog.
- Spreading-rate :10 to 12 m²/Kg in one layer. Complies with ISO 23811 (2009).
- Application equipment: Roller, spalter (flat brush) or glove.
- Density : 1.19 +/- 0.05 depending on the color at 25 ° C. in accordance with standard NM ISO 2811-1 (2008).
- Viscosity : 300 +/- 350 poises at 25 ° C.

SURFACE PREPARATION

The work must be done in accordance with standard NF DTU59.1 and will be carried out with the greatest care.

CONDITIONS AND METHODS OF APPLICATION

Prepare your walls.
 1-Apply 1 layer of Colofondo and let dry for 12 hours. 2- Apply a 1st coat of Tilal using a roller; brush; or gloves.
 3-After 4 hours, apply a 2nd coat of Tilal, with an ATF brush, according to the desired finish (alternately, diagonal, horizontal, circular or others).
 Application limit: Do not apply on condensing or frozen support, at temperatures below 5 ° C, and above 35 ° C, nor at relative humidity above 70%.

APPLICATION DETAILS OF USAGE

Dilution: ready to use. (can be diluted up to 5% water).
 Mix the product well with a spatula before use.

DRYING TIME

Drying at 20 ° C and 65% humidity:

- * Dry to touch: 30 minutes
- * Dry: 4 hours
- * Interval between coats: 4 hours
- * Washable after: 20 days

RECOMMENDED SYSTEM

■ INTERIOR

SYSTEM	NUMBER OF COATS
COLOPRIM or COLOFIX	1
COLENDUIT Extra B505 or SP88	2
COLOFONDO	1
Tilal	2

STORAGE

The product can be stored for up to 2 years in good storage conditions away from sunlight, it is nevertheless recommended to shake the product before use.

PACKAGING

2,5 kg.

HEALTH & SAFETY

Health and safety information and precautions for use are detailed on the safety data sheet N° 191 .

Edition : July 2020 by Colorado 07/20 (DC28 D).

N.B : The purpose of this technical data sheet is to provide information on the properties of our product. The information contained therein is based on our current knowledge of tests carried out with a constant concern for objectivity according to the conditions of use in accordance with standards or DTU in force; However, the information cannot replace an appropriate description and the state of the funds to be painted. This descriptive technical sheet cancels and replaces any sheet relating to the same product. The above technical data does not imply acceptance of the guarantees. Close the pot tightly after use. Help preserve the environment by not disposing of waste in the drains or household waste. Please return your empty jar to a recycling center. For your unused product, please contact your local authorities for information on disposal and collection.

COLORADO is certified ISO 9001, ISO 14001 and ISO 45001